

**Review**

# A Review on Characterization of Hybrid Fibre Reinforced Polymer Composite

M. K. Gupta<sup>1\*</sup>, R. K. Srivastava<sup>1</sup>

<sup>1</sup> Department of Mechanical Engineering,

Motilal Nehru National Institute of Technology Allahabad- 211004, India

**Abstract**

Fibre reinforced polymer composite are well recognized materials for automobile, aerospace, packaging and construction industries due to its properties such as light weight, low cost and high specific strength. Hybridization of fibres has become very popular technique to increase the properties of single fibre reinforced polymer composite. This paper presents review on mechanical properties, thermal properties, water absorption properties, dynamic mechanical analysis and tribological behaviour of hybrid fibre reinforced polymer composite. Finding of this study shows that hybridization can improved mechanical, thermal and dynamic mechanical property, and decrease water absorption property and wear rate.

**Keywords:** Hybrid; Natural fibre; Polymer; Characterization

**Academic Editor:** Taihong Shi, PhD, Sun Yat-sen University, China

**Received:** October 14, 2015; **Accepted:** December 29, 2015; **Published:** March 29, 2016

**Competing Interests:** The authors have declared that no competing interests exist.

**Copyright:** 2016 Gupta MK. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

**\*Correspondence to:** M. K. Gupta, Department of Mechanical Engineering, Motilal Nehru National Institute of Technology Allahabad, India

**E-mail:** mnnit.manoj@gmail.com

## 1. Introduction

Fibre reinforced polymer composite is consist of either synthetic or natural fibre as reinforcement and polymer as matrix. Synthetic fibre like glass, carbon and aramid has been frequently used in aerospace and automobile industries due to low density, high stiffness and strength. In spite of these properties of synthetic fibre, they have serious drawbacks like biodegradability, recyclability, initial processing cost and health hazards etc. Natural fibres like jute, banana, sisal, hemp etc. have potential to replace these synthetic fibres for environmental concern due to its properties such as lightweight, low cost, environmental friendly, high flexibility, renewability, biodegradability, high specific strength, high toughness, and easy processing [1-8]. Natural fibres also suffer by some limitations like low strength and high water absorption property. These limitations can be improved by using hybridization technique. Hybrid composite are those which have more than one reinforcement in a single matrix or single reinforcement with multiple matrix or multiple reinforcement with multiple matrix. Hybridization can increase the mechanical properties of single fibre polymer composite due to following reason:

- In hybridization, two types of fibres having same length but with different diameters into a polymer matrix provides some advantages over the use of one fibre in the composites. Different diameters of fibres increased the effective area for fibres matrix adhesion so that uniform transfer of stress could take place [9].
- In hybridization two different fibres are used with their different modulus. The high modulus fibre provides the stiffness and load bearing capacity whereas low modulus fibre provides more damage tolerant and reduced the material's cost [10].
- In hybridization two different fibres are used with their different elongation at break. The fibre having low elongation will break first and then the load may be carried by the fibre having high elongation without the failure of matrix, inducing better stress transfer from matrix to fibres and thus resulting in increased mechanical properties [11].

In this review, mechanical properties, dynamic mechanical analysis, thermal properties, water absorption property and tribological property of hybrid fibre reinforced polymer composite are discussed.

## 2. Characterization of hybrid fibre reinforced polymer composite

### 2.1 Mechanical properties of hybrid fibre reinforced polymer composite

Many researchers have added synthetic fibre with natural fibre reinforced polymer composite and they found positive result of hybridization in terms of increase in mechanical properties of single natural fibre reinforced polymer composite [12-15]. Kumar et al. [16] studied the effect of glass fibre loading with banana fibre reinforced polypropylene composite. The hybrid composite is prepared by injection moulding process with various weight fractions of fibres. They reported that the mechanical properties are improved due to incorporation of glass fibres with banana composite. AlMaadeed et al. [17] studied the effect of addition of glass fibre with date palm wood flour reinforced hybrid polypropylene composites. They found increase in tensile strength and tensile modulus of date palm polypropylene composite due to reinforcement of glass fibres.

Many researchers [18-22] have also used additional high strain natural fibre with natural fibre reinforced polymer composite. It is observed that addition of high strain natural fibre have increased the mechanical properties of single natural fibre reinforced polymer composite. Shanmugam et al. [23] investigated the

effect of jute fibre loading on mechanical properties of unidirectional palm stalk fibre reinforced polyester composite. They found that addition of jute fibre into palm fibre reinforced polyester composite has increased its mechanical properties. Boopalan et al. [24] investigated the effect of jute fibre loading on mechanical properties of banana fibre reinforced epoxy composites. They found its positive effect in terms of increased mechanical properties of banana composite. Venkateshwaran et al. [25] fabricated banana/sisal reinforced epoxy composite and studied its mechanical properties. They found that hybrid sisal and banana composites show the better mechanical properties than single banana and sisal composite.

## 2.2 Dynamic mechanical properties of hybrid fibre reinforced polymer composite

Dynamic mechanical analysis has become a far used technique to determine the interfacial characteristics of natural fibre reinforced polymer composite. Many researchers have reported studies on dynamic mechanical analysis of natural fibres reinforced polymer composites. Idicula et al. [26] reported study on the dynamic mechanical analysis of hybrid banana /sisal fibre reinforced polyester composites. Dynamic mechanical analysis of hybrid composite is evaluated in terms of storage modulus, loss modulus and damping factor using three point bending test, within temperature range 30-150 °C at different frequencies. At 40 vol. % fibre content the storage modulus and peak width of  $Tan\delta$  is found the maximum but the  $Tan\delta$  height is the minimum. Shanmugam et al. [23] proposed study on dynamic mechanical properties of alkali treated hybrid palmyra palm leak stalk / jute fibre reinforced polyester composite. The results indicated that addition of jute fibres to palmyra palm leak stalk fibre and alkali treatment of fibres has enhanced storage and loss modulus. The maximum damping behavior is observed for composite with higher jute fibre content. Jawaid et al. [19] studied the dynamic mechanical analysis of hybrid jute/oil palm epoxy composite. Storage modulus of palm fibre reinforced epoxy composite is increased due to incorporation of jute fibres while damping factor shifts toward higher temperature.

## 2.3 Thermal properties of hybrid fibre reinforced polymer composite

Thermal analysis of composite is used to find out the thermal stability of composites. Kasama et al. [27] studied the thermal properties of sisal/glass fibre reinforced polypropylene composite. It is reported that the decomposition temperature is increased with increasing glass fibre contains in composites. Boopalan et al. [9] studied the thermal properties of hybrid jute/banana fibre reinforced epoxy composite. They suggested that the hybrid composite (50% jute and 50% sisal of 30 wt. %) shows the higher thermal stability as compared to others composites. Jawaid et al. [28] reported the studies on thermal properties of hybrid oil palm/woven jute fibre reinforced epoxy composite. Addition of woven jute fibres in oil palm fibre reinforced epoxy composite increased its thermal stability. Naidu et al. [29] studied the thermal properties of sisal/glass fibre reinforced polyester composite. Thermal conductivity of hybrid sisal/glass fibre is found higher than sisal reinforced composite but lower than glass fibre reinforced polyester composite. Dhakal et al. [30] reported studies on thermal properties of hybrid hemp/glass fibre reinforced polyester composite. They reported that the hybrid composite shows better thermal stability as compared to other composites. Saw et al. [31] reported study on thermal properties of hybrid jute/bagasse fibre reinforced epoxy composite. They suggested that the hybrid composites show better thermal stability than other single fibre composites.

## 2.4 Water absorption properties of hybrid fibre reinforced polymer composite

Water absorption properties of composites are reported by different researchers and found that hybridization can decrease the water absorption properties of single fibre reinforced polymer composite. Venkateshwaran et al. [25] investigated the water absorption properties of hybrid banana/sisal fibre reinforced epoxy composite. It is observed that the addition of sisal fibre in banana fibre reinforced composite of up to 50 %

results in decreasing the water absorption properties. Thwe et al. [32] investigated the environmental behavior of hybrid bamboo/glass fibre reinforced polypropylene composite. The moisture absorption level of bamboo fibre reinforced polypropylene samples is found higher than hybrid bamboo/glass fibre reinforced polymer composites. Moisture gain decreased with increasing the glass fibres content in the composite. Mishra et al. [33] investigated the water absorption behavior of (palm/sisal)/glass fibre reinforced polyester hybrid composites with different weight percentage of fibres. They reported that the water absorption property of hybrid composites is found lower than unhybrid composites. Velmurugan et al. [34] investigated the water absorption behavior of randomly oriented hybrid palmyra/glass fibre composites with different weight fractions of fibre content. Addition of glass fibre with palmyra fibre in the matrix decreases the moisture absorption properties of the composites. Kushwaha et al. [35] investigated the water absorption behavior of the bamboo/glass fibre reinforced epoxy and polyester matrix hybrid composites. The hybrid composite shows the lower moisture uptake from 26% to 16% compared to bamboo fibre polyester composite.

### 2.5 Tribological properties of hybrid fibre reinforced polymer composite

Tayeb [36] explained the tribological behavior of sugarcane and glass polyester composite. He suggested that the sugarcane polyester composite shows better degree of wear resistance and friction coefficient as compared to glass fibre reinforced polyester composite. Kumar et al. [37] investigated the frictional coefficient of hybrid sisal/glass fibre reinforced epoxy composites with different sliding speeds such as 0.2, 2 and 4 mm/s with constant applied load of 10 N. The results indicates that the increasing the fibre length of the composites the frictional coefficient is found to increased. The optimal improvement is found at 2 cm treated fibre reinforced composites compared to untreated ones. Biswas et al. [38] investigated the erosion wear behavior of short bamboo/E-glass fibre reinforced epoxy hybrid composites with various weight compositions. The result of erosion rate versus impact velocity curve reported that 15 wt. % bamboo/glass fibre reinforced composites shows the least erosion rate compared to other composites.

## 3. Conclusions

The mechanical properties, dynamic mechanical analysis, thermal property, water absorption property and tribological property of hybrid fibre polymer composite are discussed and following conclusions are reported.

- Mechanical properties like tensile, flexural and impact property of single fibre reinforced polymer composite can be improved using hybridization technique.
- Dynamic mechanical properties such as storage modulus, loss modulus, damping and glass transition temperature are found to improve due to hybridization.
- Thermal property of single fibre reinforced polymer composite can be also increased due to hybridization.
- Wear rate, coefficient of friction and water absorption property of single fibre reinforced polymer composite are found to decrease due to hybridization.

## Acknowledgement

This work has no any support from any funding agency.

## References

1. Gupta MK, Srivastava R K. Potential of jute fibre reinforced polymer composites: A Review, *I J Fib Text Res.* 2013, 45:619-624
2. Gupta MK, Srivastava RK. Effect of sisal fibre loading on wear and friction properties of jute fibre reinforced epoxy composite. *Americ J Polym Sci Eng.* 2015, 3:197-208
3. Gupta MK, Srivastava RK. Effect of sisal fibre loading on dynamic mechanical analysis and water absorption behaviour of jute fibre epoxy composite. *Mater Today: Proceed.* 2015, 2:2909-2917
4. Muralidhar BA. Study of flax hybrid performs reinforced epoxy composite. *Mater Des.* 2013, 52:835-840
5. Huda MS, Drzal LT, Mohanty AK, Misra M. Chopped glass and recycled news paper as reinforcement fibres in injection molded poly (lactic acid) (PLA) composites: A comparative study. *Compos Sci Technol.* 2006, 66:1813-1824
6. Ramnath BV, Kokan SJ, Raja RN, Sathyanarayanan R, Elanchezhian C, Prasad AR, Manickavasagam VM. Evaluation of mechanical properties of abaca-jute-glass fibre reinforced epoxy composite. *Mater Des.* 2013, 366:357-366
7. Bakare IO, Okieimen FE, Pavithran C, Khalil HPSA, Brahmakumar M. Mechanical and thermal properties of sisal fibre-reinforced rubber seed oil-based polyurethane composites. *Mater Des.* 2010, 31:4274-4280
8. Yan L, Chouw N, Jayaraman K. flax fibre and its composites- A review. *Compos Part B* 2014, 56:296-317
9. Boopalan M, Niranjana M, Umapathy MJ. Study on the mechanical properties and thermal properties of jute and banana Fibre reinforced epoxy hybrid composites. *Compos Part-B.* 2013, 51:54-57
10. Kedar S, Pandya Ch, Veerraju, Naik NK. Hybrid composites made of carbon and glass woven fabrics under quasi - static loading. *Mater Desi* 2011, 32:4094-4099
11. Sreekala MS, George J, Kumaran MG, Thomas S. The mechanical Performance of hybrid phenol-formaldehyde - based composites reinforced with glass and oil palm fibres. *Compos Sci Technol.* 2002, 62:339-353
12. HazizanAkil MD, Santulli C, Sarasini F, Tirillò, Valente T. Environmental effects on the mechanical behaviour of pultruded jute/glass fibre-reinforced polyester hybrid composites. *Compos Sci Technol.* 2014, 94:62-70
13. Arthanarieswaran, VP, Kumaravel A, Kathirselvam M. Evaluation of mechanical properties of banana and sisal Fibre reinforced epoxy composites Influence of glass Fibre hybridization. *Mater Desi.* 2014, 64:194-202
14. SabeelAhmed, K.; Vijayarangan, S. Tensile, flexural and interlaminar shear properties of woven jute and jute-glass fabric reinforced polyester composites. *J Mater Proces Technol* 2008, 2017:330-335
15. Zhang Y, Li Y, Ma H, Yu T. Tensile and interfacial properties of unidirectional flax/glass Fibre reinforced hybrid composites. *Compos Sci Technol.* 2013, 88:172-177
16. Kumar, N.R.; Prasad, G.R.; Rao, B.R. Investigation on mechanical properties of banana fibre glass reinforced hybrid thermoplastic composites. *Int J Eng Res Technol.* 2013, 2 (11):3701-3706
17. AlMaadeed MA, Kahraman R, Khanam PN, Madi N. Date palm wood flour/glass fibre reinforced hybrid composites of recycled polypropylene Mechanical and thermal properties. *Mater Desi.* 2012, 42:289-294

18. Jawaaid M, Khalil HPSA, Bakar AA. Mechanical performance of oil palm empty fruit bunches/jute fibres reinforced epoxy hybrid composites. *Mater Sci Eng.* 2010, 527:7944-7949
19. Jawaaid M, Khalil HPSA, Hassan A, Dungani R, Hadiyani A. Effect of jute fibre loading on tensile and dynamic mechanical properties of oil palm epoxy composites. *Compos Part-B.* 2013, 45:619-624
20. Santulli C, Sarasini F, Tirillò J, Valente T, Valente M, Caruso AP, Infantino M, Nisini E, Minak G. Mechanical behaviour of jute cloth/wool felts hybrid laminates. *Mater Desi.* 2013, 50:309-321
21. Alavudeen A, Rajini N, Karthikeyan S, Thiruchitrabalam M, Venkateshwareen N. Mechanical properties of banana/Kenaf Fibre-reinforced hybrid polyester composites Effect of woven fabric and random orientation. *Mater Desi.* 2015, 66:246-257
22. Asaithambi B, Ganesan G, Ananda Kumar S. Bio-composites Development and Mechanical Characterization of Banana/Sisal Fibre Reinforced Poly Lactic Acid. PLA; Hybrid Composites. *Fib Polym.* 2014, 15:847-854
23. Shanmugam D, Thiruchitrabalam M. Static and dynamic mechanical properties of alkali treated unidirectional continuous Palmyra Palm Leaf Stalk Fibre/jute Fibre reinforced hybrid polyester composites. *Mater Desi.* 2013, 97:533-542
24. Boopalan M, Niranjana M, Umapathy MJ. Study on the mechanic properties and thermal properties of jute and banana Fibre reinforced epoxy hybrid composites. *Compos Part-B.* 2013, 51:54-57
25. Venkateshwaran N, ElayaPerumal A, Alavudeen A, Thiruchitrabalam M. Mechanical and water absorption behaviour of banana/sisal reinforced hybrid composites. *Mater Desi* 2011, 32:4017-4021
26. Idicula M, Malhotra SK, Josheph K, Thomas S. Dynamic mechanical analysis of randomly oriented intimately mixed short banana /sisal fibre reinforced polyester composites. *Compos Sci Technol.* 2005, 65:1077-1087
27. Kasama Jarukumjorn, Nitinat Suppakarn. Effect of glass fibre hybridization on properties of sisal fibre-polypropylene composites. *Compos Part-B.* 2009, 40:623-627
28. Jawaaid M, Abdul Khalil HPS, Alattas OS. Woven hybrid bicomposites: dynamic mechanical and thermal properties. *Compos Part-A.* 2012, 43:288- 293
29. Naidu VNP, Kumar AM, Ramachandra RG. Thermal conductivity of sisal/glass fibre reinforced hybrid composites. *Inter J Fib Tex.* 2011, 1:28-30
30. Dhakal HN, Zhang ZY, Bennett N. Influence of fibre treatment and glass fibre hybridization on thermal degradation and surface energy characteristics of hemp/unsaturated polyester composites. *Compos Part-B.* 2012, 43:2757-2761
31. Saw SK, Datta C. Thermomechanical properties of jute/bagasse hybrid fibre reinforced epoxy thermoset composites. *Biores.* 2009, 4:1455-1476
32. Thwe MM, Liao K. Durability of bamboo glass fibre reinforced polymer matrix hybrid composites. *Compos Sci Technol.* 2003, 63:375-387
33. Mishra S, Mohanty AK, Drzal LT. Studies on mechanical performance of biofibre/glass reinforced polyester hybrid composites. *Compos Sci Technol.* 2003, 63:1377-1387
34. Velmurugan R, Manikandan V. Mechanical properties of palmyra/glass fibre hybrid composites. *Compos Part-A.* 2007, 38:2216-2226
35. Kushwaha PK, Kumar R. The studies on performance of epoxy and polyester-based composites reinforced with bamboo and glass fibres. *J Reinf Plast Compos.* 2010, 29:1952-1962

36. Tayeb NSME. A study on the potential of sugarcane fibres/polyester composite for Tribological applications. **Wear**. 2008, 265:223-235
37. Kumar AM, Ramachandra RG, Bharathi SY. Frictional coefficient, hardness, impact strength and chemical resistance of reinforced sisal-glass fibre epoxy hybrid composites. **J Compos Mater**. 2010, 44:3195-3202
38. Biswas S, Xess PA. Erosion wear behaviour of bamboo/glass fibre reinforced epoxy based hybrid composites. **Int Conf Mech Indus Eng**, Darjeeling, West Bengal, India, 27 May- 2012